

SIKA Sverige AB
Sebastian Lejonmark
Box 8061
163 08 Spånga

Resistance to static loading of SARNAFIL TS 77-15ER

Product

SARNAFIL TS 77-ER15 roof waterproofing membrane.

Commission

To test resistance to static loading according to EN12730:2015 method A and method C.

Sample

One roll of SARNAFIL TS 77-ER15 arrived to SP Technical Research Institute of Sweden 19th of November 2015.

Test procedure and results

The test was performed according to EN 12730:2015 method A (indentation of 40 mm) and method C (indentation of 10 mm). The soft support used for the tests was EPS CS(10)150 and the duration was 24 h.

The results from the tests are presented in the table below.

Properties	Test method	Results	Date of test	Requirement
Resistance to static load	EN 12730:2015 Method A	Tight at 20 kg	2 Feb 2016	Tight at 20 kg
Resistance to static load	EN 12730:2015 Method C	Tight at 20 kg	3 Feb 2016	Tight at 20 kg

SP Technical Research Institute of Sweden

Postal address
SP
Box 857
SE-501 15 BORÅS
Sweden

Office location
Västeråsen
Brinellgatan 4
SE-504 62 BORÅS

Phone / Fax / E-mail
+46 10 516 50 00
+46 33 13 55 02
info@sp.se

Laboratories are accredited by the Swedish Board for Accreditation and Conformity Assessment (SWEDAC) under the terms of Swedish legislation. This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.



SP Technical Research Institute of Sweden
SP Chemistry, Materials and Surfaces - Polymer and Fiber (KMp)

Performed by

Examined by

Karin Agrenius

Elin Johnsson