

PRODUCT DATA SHEET

Sika MonoTop®-910 Eco

BONDING PRIMER AND REINFORCEMENT CORROSION PROTECTION CEMENT BASED SLURRY WITH REDUCED CARBON FOOTPRINT

DESCRIPTION

Sika MonoTop®-910 Eco is a 1-part, cementitious, polymer modified coating material used as bonding primer and reinforcement corrosion protection. It is specially formulated to contain recycled waste materials to reduce its carbon footprint.

USES

- Bonding primer as part of a concrete repair system
- Reinforcement corrosion protection as part of a concrete repair system
- Suitable for control of anodic areas (Principle 11, method 11.1 of EN 1504-9)

CHARACTERISTICS / ADVANTAGES

- Lower carbon footprint
- Easy to use, just add water
- Good adhesion to concrete and steel
- Good resistance to water and chloride penetration
- Can be applied with a brush or by wet spray technique

SUSTAINABILITY

- Conformity with LEED v4 MRc 2 (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations

APPROVALS / CERTIFICATES

CE Marking and Declaration of Performance to EN 1504-7- Product for reinforcement corrosion protection

PRODUCT INFORMATION

Composition	Portland cement, cement replacement, re-dispersible polymer powder, selected aggregates and additives	
Packaging	25 kg bag Refer to current price list for packaging variations.	
Appearance / Colour	Grey powder	
Shelf life	12 months from date of production	
Storage conditions	Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C. Always refer to packaging.	
Soluble Chloride Ion Content	≤ 0,01 %	(EN 1015-17)
Product Declaration	Pass	(EN 1504-7)

TECHNICAL INFORMATION

Compressive Strength	~50 MPa after 28 days	(EN 12190)
Tensile Adhesion Strength	~2,0 MPa after 28 days	(EN 1542)
Shear Adhesion Strength	Pass	(EN 15184)
Diffusion Resistance to Water Vapour	~100 µH ₂ O	
Diffusion resistance to carbon dioxide	~1200 µCO ₂	
Corrosion Test	Pass	(EN 15183)

SYSTEMS

System Structure	Sika MonoTop®-910 Eco is part of the range of Sika Mortars and comprising of:	
	Bonding Primer/ Reinforcement	
	Corrosion Protection	
	Sika MonoTop®-910 Eco	Reduced carbon footprint
Repair Mortar		
	Sika MonoTop®-412 Eco	Reduced carbon footprint

APPLICATION INFORMATION

Mixing Ratio	For brush application	~5,25 L water (21 %) per 25 kg bag
	For spraying application	~5,0 L water (20 %) per 25 kg bag
Fresh Mortar Density	~2.0 kg/l	
Consumption	Bonding Primer	~1,5–2,0 kg of powder per m ² per 1 mm layer thickness Depends on substrate roughness and thickness of layer applied
	Reinforcement Corrosion Protection	~2,0 kg of powder per m ² per 1 mm layer thickness
Yield	~14,3 L per 25 kg of powder	
Layer Thickness	Bonding primer- sufficient to coat the concrete surface in a thin layer filling pores and voids. Reinforcement corrosion protection - 2 mm minimum thickness.	
Ambient Air Temperature	+5 °C min. / +30 °C max	
Substrate Temperature	+5 °C min. / +30 °C max	
Pot Life	~90 minutes for 20 % water (machine applied). ~120 minutes for 21 % water (manual application).	
Waiting Time / Overcoating	Apply concrete repair mortar wet on wet with bonding primer. Apply concrete repair mortar wet on dry reinforcement corrosion protection.	

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete

The concrete must be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials. De-laminated, weak, damaged and deteriorated concrete and where necessary

sound concrete must be removed by suitable means. Ensure sufficient concrete is removed from around corroded reinforcement to allow cleaning for corrosion protection (where required) and compaction of the repair material.

Steel reinforcement

Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion must be removed. Surfaces must be prepared using abrasive blast cleaning techniques or

high pressure water-blasting to Sa 2 (ISO 8501-1). Reference must be made to EN 1504-10 for specific requirements.

MIXING

Mixed with a low speed (< 500 rpm) hand drill mixer or by hand for small quantities. Pour the recommended water quantity in a suitable mixing container. While stirring slowly, add the powder to the water and mix thoroughly for at least for 3 minutes.

APPLICATION

Bonding primer

Thoroughly pre-wet the prepared substrate a recommended 2 hours before application. Keep the surface wet and do not allow to dry. Before application remove excess water e.g. with a clean sponge. The surface must appear a dark matt appearance without glistering. Surface pores and voids must not contain water. Using a suitable clean brush, roller or suitable spraying equipment, cover the substrate in a thin layer filling all unevenness, pits and voids.

Reinforcement corrosion protection

Using a suitable clean brush or spraying equipment, apply a first coat to cover the reinforcement bars ~1 mm thick. When first coat is finger nail hard, apply a second layer ~1 mm thick. If using a spray method, protect substrate from excessive over-spray. Wait until completely dry before applying repair mortar.

CURING TREATMENT

Reinforcement corrosion protection: protect fresh coating immediately from premature drying and contamination using an appropriate curing method.

CLEANING OF EQUIPMENT

Clean all tools and equipment with water immediately after use. Hardened material can only be mechanically removed.

FURTHER INFORMATION

- Sika MonoTop® Method Statement: Concrete Repair Using Sika MonoTop® System
- EN 1504-7 - Reinforcement corrosion protection

IMPORTANT CONSIDERATIONS

- Avoid application in direct sun and/or strong wind and/or rain.
- Do not add water over recommended dosage.
- Apply only to sound, prepared substrates.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.